

Article

Gas-Phase Synthesis of Dimethyl Carbonate from Methanol and Carbon Dioxide Over $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ Keggin-Type Heteropolyanion

Ahmed Aouissi *, Zeid Abdullah Al-Othman and Amro Al-Amro

Department of Chemistry, King Saud University, P.O. Box 2455, Riyadh-11451, Saudi Arabia

* Author to whom correspondence should be addressed; E-Mail: aouissed@yahoo.fr.

Received: 22 January 2010; in revised form: 9 March 2010 / Accepted: 29 March 2010 /

Published: 31 March 2010

Abstract: The reactivity of $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ in the direct synthesis of dimethyl carbonate (DMC) from CO_2 and CH_3OH was investigated. The synthesized catalyst has been characterized by means of FTIR, XRD, TG, and DTA and tested in gas phase under atmospheric pressure. The effects of the reaction temperature, time on stream, and methanol weight hourly space velocity (MWHHSV) on the conversion and DMC selectivity were investigated. The highest conversion (7.6%) and highest DMC selectivity (86.5%) were obtained at the lowest temperature used (200 °C). Increasing the space velocity MWHHSV increased the selectivity of DMC, but decreased the conversion. A gain of 18.4% of DMC selectivity was obtained when the MWHHSV was increased from 0.65 h^{-1} to 3.2 h^{-1} .

Keywords: heteropolyanion; Keggin structure; methanol; dimethyl carbonate; direct synthesis; carbon dioxide

1. Introduction

Dimethyl carbonate (DMC) has drawn much attention in recent years as an environmentally friendly versatile intermediate. It has been used as a good solvent [1], an alkylation agent [2], and a substitute for highly toxic phosgene and dimethyl sulfate in many chemical processes [3,4]. In addition, it is expected to replace the gasoline oxygenate methyl *tert.* butyl ether (MTBE), because of its high oxygen content, low toxicity, and rapid biodegradability [1,5,6]. DMC has been produced by the reaction of methanol with phosgene in a concentrated sodium hydroxide solution [7]. However,

owing to the high toxicity and the severe corrosivity of phosgene, this process has been abandoned gradually. Currently, DMC is produced mainly by oxidative carbonylation of methanol (non-phosgene route) [8]. The synthesis can be carried out in both liquid- and gas-phases. However, both routes use poisonous gas carbon monoxide and there is the possibility of an explosion. Recently, direct synthesis of DMC from CO_2 and CH_3OH has been reported as a most attractive route due to the low-cost of CO_2 and the environmentally benign process [9–14]. However, DMC yield in this route is relatively low due to the fact that CO_2 is thermodynamically stable and kinetically inert and due to the deactivation of catalysts induced by water formation in the reaction process [10,15]. Therefore, the development of efficient heterogeneous catalytic systems has attracted more attention. Bian *et al.* [16] studied the reaction over Cu–Ni/graphite nanocomposite catalyst in gaseous phase. They obtained 10.13% of CH_3OH conversion and 89.04% of DMC selectivity at 105 °C. Wu *et al.* [17] studied the synthesis of DMC from gaseous methanol and CO_2 over H_3PO_4 modified V_2O_5 catalyst with various molar ratios $\text{H}_3\text{PO}_4/\text{V}_2\text{O}_5$ (P/V). The best conversion (1.95%) and selectivity of DMC (92.12%) was obtained at 130 °C on the catalyst $\text{H}_3\text{PO}_4/\text{V}_2\text{O}_5$ (P/V = 0.20).

Here we report the direct synthesis of DMC from methanol and CO_2 in gas phase over $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ as a Keggin-type heteropolyanion catalyst. The effect of the reaction temperature, MWHSV, and time on stream on DMC synthesis was investigated.

2. Results and Discussion

2.1. Characterization of Catalysts

The FT-IR spectrum of the $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ is shown in Figure 1. The IR spectrum has been assigned according to [18,19]. The main characteristic features of the Keggin structure are observed at 1080–1060 cm^{-1} , 990–960 cm^{-1} , 900–870 cm^{-1} , and 810–760 cm^{-1} , assigned to the stretching vibration ν_{as} (P-O_a), ν_{as} (M-O_d), ν_{as} ($\text{M-O}_c\text{-M}$), and ν_{as} ($\text{M-O}_c\text{-M}$), respectively ($\text{M} = \text{W}$ or Mo). The result of X-ray powder diffraction of the $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ salt is shown in Figure 2. In each of the four ranges of 2θ , 7°–10°, 16°–23°, 25°–30°, and 31°–38°, the compound shows a characteristic for well defined Keggin structure of heteropolyanions [20–22]. So the presence of the primary Keggin structure in the synthesized phases was confirmed by FTIR and XRD.

Figure 1. IR spectrum of $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ Keggin-type heteropolyanion.






Figure 2. XRD pattern of $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ Keggin-type heteropolyanion.**Figure 3.** Differential thermal analysis (DTA) and thermo-gravimetric analysis (TGA) of $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ (heating rate: 5 °C /min).

Thermogravimetric (TG) and Differential Thermal Analysis (DTA)

Thermogravimetric analysis of $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ (Figure. 3) showed that the dehydration process starts at low temperature, about 50 °C, and finishes at 250 °C. The differential thermal analysis (DTA) indicates two endothermic peaks below 250 °C, and an exothermic peak at 575 °C. In agreement with the TG results, the endothermic peaks are assigned to the removal of physisorbed or crystallization water molecules (13-14 H_2O), whereas the exothermic peak is due to the decomposition of $\text{Co}_{1.5}\text{PW}_{12}\text{O}_{40}$ into the corresponding oxides ($3/2\text{CoO}$, 12WO_4 and $1/2\text{P}_2\text{O}_5$). This result is in agreement with published results [23].

2.2. Catalytic Reaction

2.2.1. Effect of Reaction Temperature

The effect of the reaction temperature on the reaction performance was investigated at temperatures ranging from 200–300 °C. The results are illustrated in Figure 4 and 5. It can be seen from Figure 4 that CH₃OH conversion and product yields decreased dramatically with increasing temperature. The decrease of both the conversion and product yields with increasing temperature might be due to the decreased CO₂ adsorption on the catalyst at high temperatures [10]. Figure 5 shows that the selectivity of DMC decreased with increasing temperature. The decrease of DMC selectivity is probably due to the decomposition of DMC at higher temperatures [10,16, 24–26]. It can be seen from these results that the highest conversion of 7.6% and highest selectivity of DMC of 86.5% was obtained at the lowest temperature in this range of temperatures (200 °C).

Figure 4. The dependence of the conversion and product yields on reaction temperature over Co_{1.5}PW₁₂O₄₀. Reaction conditions: MWHSV = 3.25 h⁻¹; molar ratio CH₃OH /CO₂ = 1.9.





Figure 5. The dependence of the conversion and product selectivity on reaction temperature over Co_{1.5}PW₁₂O₄₀. Reaction conditions: MWHSV = 3.25 h⁻¹; molar ratio CH₃OH /CO₂ = 1.9.



2.2.2. Effect of Time on Stream

Figure 6 shows CH_3OH conversion and products yield as a function of time on stream. It can be seen that both CH_3OH conversion and DMC yield increased rapidly during the first three hours, then after increased slowly. DMM and MF were observed as minor products with a rate formation almost constant. As for the product selectivity, it can be seen from the figure 7 that DMC selectivity increased slightly with increasing time on stream to the detriment of DMM and MF.

Figure 6. Time on stream effect on the conversion and product yields. Reaction conditions: $T = 200\text{ }^\circ\text{C}$; $\text{MWHSV} = 3.25\text{ h}^{-1}$; molar ratio $\text{CH}_3\text{OH}/\text{CO}_2 = 1.9$.





Figure 7. The product selectivities as a function of time on stream. Reaction conditions: $T = 200\text{ }^\circ\text{C}$; $\text{MWHSV} = 3.25\text{ h}^{-1}$; molar ratio $\text{CH}_3\text{OH}/\text{CO}_2 = 1.9$.




2.2.3. Effect of Space Velocity

The effect of methanol weight hourly space velocity (MWHSV) on the conversion of methanol and the selectivity of DMC is shown in Figure 8. It can be seen that the conversion dropped sharply to about 6.4%. In fact, when the SV changed from 0.6 h^{-1} to 1.6 h^{-1} , the conversion decreased from 15.7% to 9.3%. Further increase of MWHSV did not influence the conversion of methanol considerably. The conversion dropped only to about 1.7%. In fact, it has been found that when the MWHSV changed from 1.6 h^{-1} to 3.2 h^{-1} , the conversion decreased from 9.3% to 7.6%. As for the selectivity of DMC, the

result showed that increasing the MWHSV from 0.65 h⁻¹ to 3.2 h⁻¹ increased the selectivity from 68.1% to 86.5% gaining in this way 18.4% of DMC selectivity.

Figure 8. Conversion and DMC selectivity over Co_{1.5}PW₁₂O₄₀ as a function of MWHSV. Reaction conditions: T = 200 °C; molar ratio CH₃OH /CO₂ = 1.9.



3. Experimental Section

3.1. Catalyst Preparation

The heteropolymolybdate salt namely Co_{1.5}PW₁₂O₄₀ was prepared from 12-tungstophosphoric acid H₃PW₁₂O₄₀ as precipitate by adding slowly the required amount of CoCO₃. After protons neutralization by CO₃²⁻, the cobalt salt, Co_{1.5}PW₁₂O₄₀ was recovered from the solution by filtration

3.2. Physicochemical Techniques

The purity and the Keggin structure of the samples were characterized by means of IR and XRD. IR spectra were recorded with an infrared spectrometer GENESIS II-FTIR (400–4000 cm⁻¹) as KBr pellets. The XRD powder patterns were recorded on a Rigaku diffractometer Ultima IV using CuK α radiation. Thermal analysis was carried out by means of differential thermal analysis (DTA) and thermogravimetric analysis (TGA) in air atmosphere with a 50 Shimadzu thermobalancesis

3.3. Catalytic Tests

The direct synthesis of DMC from methanol and CO₂ was carried out at the temperature ranging from 200 °C to 300 °C in a flow-type fixed-bed stainless reactor loaded with 100 mg of catalyst under atmospheric pressure. To supply the reactant, a gas CO₂ at a flow rate of 60 mL min⁻¹ was passed through the methanol saturator thermostated at 40 °C. The molar ratio CO₂/CH₃OH was adjusted by the flux of CO₂ controlled by mass flow controller and the temperature of saturator. Prior to the reaction, the catalyst was pretreated at 300 °C with CO₂ for 2 h. The reaction products were analyzed

with a gas phase chromatograph (Agilent 6890N) equipped with a flame ionization detector and a capillary column (HP-PLOT Q length 30m ID 0.53 mm). The condensed liquid was collected and analyzed. Catalytic activity was indicated by CH₃OH conversion and product yields and selectivities. These parameters are calculated according to the following equations:

$$\text{Yield}_{(i)} (\%) = \frac{N_i}{N_o} \times 100$$

$$\text{Conversion} (\%) = \frac{N_r}{N_o} \times 100 = \sum \text{Yield}_{(i)}$$

$$S_i (\%) = \frac{\text{Yield}_{(i)}}{\text{Conversion}} \times 100$$

N_o: number of moles of methanol introduced (mol/h)

N_i: number of moles of the product i formed (mol/h)

N_r: number of moles of reacted methanol (mol/h)

4. Conclusion

Synthesis of DMC from CH₃OH and CO₂ has been studied in gas phase system under atmospheric pressure using Co_{1.5}PW₁₂O₄₀ as a catalyst. It was found that both CH₃OH conversion and DMC yield decreased with increasing temperature, owing to the decreased CO₂ adsorption on the catalyst at high temperatures. As for the decrease of DMC selectivity, this is probably due to the decomposition of DMC at higher temperatures.

Lower temperature leads to high selectivity of DMC to the detriment of that of DMM and MF. The optimal reaction conditions for the synthesis of DMC is lower temperature and high space velocity.

References

1. Pacheco M.A.; Marshall C.L. Review on Dimethyl carbonate manufacture and its characteristics as a fuel additive. *Energy Fuels* **1997**, *11*, 2–29.
2. Guo X.C.; Qin, Z.F.; Wang, G.F.; Wang, J.G. Critical temperatures and pressures of reacting mixture in synthesis of dimethyl carbonate with methanol and carbon dioxide. *Chin. Chem. Lett.* **2008**, *19*, 249–252.
3. Ono, Y. Catalysis in the production and reactions of dimethyl carbonate, an environmentally benign building block. *Appl. Catal. A* **1997**, *155*, 133–166.
4. Tundo, P.; Selva, M. The Chemistry of Dimethyl Carbonate. *Acc. Chem. Res.* **2002**, *35*, 706–716.
5. Richter, M.; Fait, M.J.G.; Eckelt, R.; Schneider, M.; Radnik, J.; Heidemann, D.; Fricke, R. Gas-phase carbonylation of methanol to dimethyl carbonate on chloride-free Cu-precipitated zeolite Y at normal pressure. *J. Catal.* **2007**, *245*, 11–24.
6. Delledonne, D.; Rivetti, F.; Romano, U. Developments in the production and application of dimethylcarbonate. *Appl. Catal. A: Gen.* **2001**, *221*, 241–251.
7. Shaikh, A.G.; Sivaram, S. Organic Carbonates. *Chem. Rev.* **1996**, *96*, 951–976.

8. Romano, U.; Tesei, R.; Mauri, M.M.; Reborá, P. Synthesis of Dimethyl Carbonate from Methanol, Carbon Monoxide, and Oxygen Catalyzed by Copper Compounds. *Ind. Eng. Chem. Prod. Dev.* **1980**, *19*, 396–403.
9. Choi, J.C.; Sakakura, T.; Sako, T. Reaction of Dialkyltin Methoxide with Carbon Dioxide Relevant to the Mechanism of Catalytic Carbonate Synthesis. *J. Am. Chem. Soc.* **1999**, *121*, 3793–3794.
10. Wu, X.L.; Xiao, M.; Meng, Y.Z.; Lu, Y.X. Direct synthesis of dimethyl carbonate (DMC) using Cu-Ni/VSO as catalyst. *J. Mol. Catal. A: Chem.* **2006**, *249*, 93–97.
11. Wu, X.L.; Xiao, M.; Meng, Y.Z.; Lu, Y.X. Direct synthesis of dimethyl carbonate on H₃PO₄ modified V₂O₅. *J. Mol. Catal. A: Chem.* **2005**, *238*, 158–162.
12. Jessop, P.G.; Ikariya, T.; Noyori, R. Homogeneous Catalysis in Supercritical Fluids. *Science* **1995**, *269*, 1065–1069.
13. Tundo, P.; Selva, M. The Chemistry of Dimethyl Carbonate. *Acc. Chem. Res.* **2002**, *35*, 706–716.
14. Omae, I. Aspects of carbon dioxide utilization. *Catal. Today* **2006**, *115*, 33–52
15. Bian, J.; Xiao, M.; Wang, S.J.; Lu, Y.X.; Meng, Y.Z. Novel application of thermally expanded graphite as the support of catalysts for direct synthesis of DMC from CH₃OH and CO₂. *J. Colloid. Interface Sci.* **2009**, *334*, 50–57.
16. Bian, J.; Xiao, M.; Wang, S.; Wang, X.; Lu, Y.; Meng, Y. Highly effective synthesis of dimethyl carbonate from methanol and carbon dioxide using a novel copper–nickel/graphite bimetallic nanocomposite catalyst. *Chem. Eng. J.* **2009**, *147*, 287–296.
17. Wu, X.L.; Xiao, M.; Meng, Y.Z.; Lu, Y.X. Direct synthesis of dimethyl carbonate on H₃PO₄ modified V₂O₅. *J. Mol. Catal. A: Chem.* **2005**, *238*, 158–162.
18. Rocchiccioli-Deltcheff, C.; Fournier, M.; Franck, R.; Thouvenot, R. Vibrational investigations of polyoxometalates. Evidence for anion-anion interactions in molybdenum(VI) and tungsten(VI) compounds related to the Keggin structure. *Inorg. Chem.* **1983**, *22*, 207–216.
19. Rocchiccioli-Deltcheff, C.; Fournier, M. Catalysis by Polyoxometalates. Part 3,–Influence of Vanadium (V) on the thermal Stability of 12-Metallophosphoric Acids from In Situ Infrared Studies. *J. Chem. Soc. Faraday Trans.* **1991**, *87*, 3913–3920.
20. Fournier, M.; Feumi-Jantou, C.; Rabia, C.; Herve, G.; Launay, S. Polyoxometalates Catalyst Materials: X-Ray Thermal Stability Study of Phosphorus-containing Heteropolyacids H_{3+x}PM_{12-x}V_xO₄₀.13-14H₂O (M=Mo, W; x=0-1). *J. Mater. Chem.* **1992**, *2*, 971–978.
21. Gao, R.; Chen, H.; Le, Y.; Dai, W.-L.; Fan K. Highly active and selective Cs_{2.5}H_{0.5}PW₁₂O₄₀/SBA-15 composite material in the oxidation of cyclopentane-1,2-diol to glutaric acid by aqueous H₂O₂. *Appl. Catal.* **2009**, *352*, 61–65.
22. Fuchs, V.M.; Pizzio, L.R.; Blanco, M.N. Synthesis and characterization of aluminum or copper tungstophosphate and tungstosilicate immobilized in a polymeric blend. *Eur. Polym. J.* **2008**, *44*, 801–807.
23. Cabello, C.I.; Egusquiza, M.G.; Botto, I.L.; Minelli, G. Heteropolyoxotungstates containing a wide catalytic target: reducibility and thermal stability. *Mater. Chem. Phys.* **2004**, *87*, 264–274.
24. Fu, Y.; Zhu, H.; Shen, J. Thermal decomposition of dimethoxymethane and dimethyl carbonate catalyzed by solid acids and bases. *Thermochim. Acta.* **2005**, *434*, 88–92.

25. Zhao, T.; Han, Y.; Sun, Y. Novel reaction route for dimethyl carbonate synthesis from CO₂ and methanol. *Fuel Proces. Tech.* **2000**, *62*, 187–194.
26. Wang, X.J.; Xiao, M.; Wang, S.J.; Lu, Y.X.; Meng, Y.Z. Direct synthesis of dimethyl carbonate from carbon dioxide and methanol using supported copper (Ni, V, O) catalyst with photo-assistance. *J. Mol. Catal. A: Chem.* **2007**, *278*, 92–96

© 2010 by the authors; licensee Molecular Diversity Preservation International, Basel, Switzerland. This article is an open-access article distributed under the terms and conditions of the Creative Commons Attribution license (<http://creativecommons.org/licenses/by/3.0/>).