



# Adherence of *Candida* to complete denture surfaces *in vitro*: A comparison of conventional and CAD/CAM complete dentures

Afnan F. Al-Fouzan<sup>1\*</sup>, Lamya A. Al-mejrad<sup>1</sup>, Ahmed M. Albarrag<sup>2</sup>

<sup>1</sup>Prosthetic Dental Science, College of Dentistry, King Saud University, Riyadh, Saudi Arabia

<sup>2</sup>Department of Pathology, School of Medicine, King Saud University, Riyadh, Saudi Arabia

**PURPOSE.** The goal of this study was to compare the adhesion of *Candida albicans* to the surfaces of CAD/CAM and conventionally fabricated complete denture bases. **MATERIALS AND METHODS.** Twenty discs of acrylic resin poly (methyl methacrylate) were fabricated with CAD/CAM and conventional procedures (heat-polymerized acrylic resin). The specimens were divided into two groups: 10 discs were fabricated using the CAD/CAM procedure (Wieland Digital Denture Ivoclar Vivadent), and 10 discs were fabricated using a conventional flasking and pressure-pack technique. *Candida* colonization was performed on all the specimens using four *Candida albicans* isolates. The difference in *Candida albicans* adhesion on the discs was evaluated. The number of adherent yeast cells was calculated by the colony-forming units (CFU) and by Fluorescence microscopy.

**RESULTS.** There was a significant difference in the adhesion of *Candida albicans* to the complete denture bases created with CAD/CAM and the adhesion to those created with the conventional procedure. The CAD/CAM denture bases exhibited less adhesion of *Candida albicans* than did the denture bases created with the conventional procedure ( $P < .05$ ). **CONCLUSION.** The CAD/CAM procedure for fabricating complete dentures showed promising potential for reducing the adherence of *Candida* to the denture base surface. Clinical Implications. Complete dentures made with the CAD/CAM procedure might decrease the incidence of denture stomatitis compared with conventional dentures. [J Adv Prosthodont 2017;9:402-8]

**KEYWORDS:** Complete denture; CAD/CAM; *Candida*; Adhesion; Edentulous; Roughness

Corresponding author:  
Afnan F. Al-Fouzan  
Department of Prosthodontics, College of Dentistry, King Saud University  
P O Box 89300, Riyadh 11682, Saudi Arabia  
Tel. +966118055645; e-mail, aalfouzan@ksu.edu.sa  
Received February 7, 2017/ Last Revision April 22, 2017/ Accepted July 4, 2017

© 2017 The Korean Academy of Prosthodontics  
This is an Open Access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/3.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

This research project was supported by a grant from the "Research Center of the Center For Female Scientific and Medical Colleges", Deanship of Scientific Research, King Saud University.  
The study was presented in 45th annual meeting & exhibition of the AADR 40th Annual Meeting of the CADR, March, 2016, Los Angeles, CA, USA.

## INTRODUCTION

Edentulism is a "debilitating and irreversible condition and is described as the final marker of disease burden for oral health."<sup>1,2</sup> Among older adults, edentulism is considered one of the most prevalent condition worldwide<sup>3</sup> although the percentage of tooth loss has decreased in recent years.<sup>4</sup> In the U.S., the prevalence of edentulism is 15% in patients between the ages of 65 and 74 years old and 22% in patients older than 75 years according to the National Health and Nutrition Examination Survey.<sup>3</sup> Emami *et al.*<sup>2</sup> reported that the majority of edentulous patients wear one or two complete dentures. The use of removable prostheses has increased due to the increasing number of older patients, who are the primary wearers of dentures, in the general population.<sup>4</sup> Being edentulous influences oral health

and general well-being.<sup>2</sup> The effects on oral health include impaired masticatory efficiency and denture-related oral lesions, such as angular cheilitis, traumatic ulcers and denture stomatitis (DS).<sup>5,6</sup> DS is an inflammation of the mucosa underlying a removable prosthesis.<sup>7</sup> Shulman *et al.*<sup>8</sup> conducted a study in the U.S. and found that the prevalence of DS among denture wearers was 28%.<sup>8</sup> Another epidemiological study reported that the prevalence of DS was highest among elderly and female denture wearers.<sup>9</sup> In addition, that study stated that the prevalence of DS ranged from 15% to over 70%.<sup>9</sup> Sadig<sup>10</sup> conducted a study in 2010 that reported the incidence of DS to be approximately 62%. Many factors might lead to the development of DS.<sup>11</sup> Some of these are related to systemic and immune diseases and impaired salivary flow, and others are related to the dentures themselves, such as poor denture hygiene, denture-induced trauma, roughness and the presence of pores in the acrylic surface.<sup>11</sup> Among these factors, *Candida* colonization is well established as a predisposing factor for the denture wearers experiencing development of denture stomatitis.<sup>12,13</sup> All the previously mentioned factors contribute to *Candida* colonization on denture and mucosal surfaces.<sup>10</sup> *Candida* is not harmful by itself, and studies have demonstrated that it is part of the normal flora.<sup>11</sup> There are 20 species of *Candida* among the 300 to 400 species of microorganisms in the oral cavity.<sup>14</sup> The presence of *Candida* ranges from 20% to 50% in healthy dentate individuals.<sup>15,16</sup> Becoming edentulous and wearing dentures both cause changes in the oral microbial flora, which lead to an increase in *Candida* colonization as high as 60% to 100%.<sup>11,17</sup> *Candida* has the ability to grow on targeted surfaces in several ways.<sup>18</sup> One of the ways is the formation of biofilms, which are significant causes of infection.<sup>18</sup> The adhesion of *Candida* to the oral mucosa is an important factor in the resistance to host clearance mechanisms in the oral cavity. Among other *Candida* species, *Candida albicans* is the most prevalent isolated species in DS, followed by *Candida glabrata*.<sup>9,11,12,19</sup> Other *Candida* species, such as *Candida krusei*, *Candida Kefyr*, *Candida parapsilosis*, and *Candida tropicalis*, occur at lower prevalences.<sup>9,11,12</sup> In addition to adhesion to the oral mucosa, the adhesion of *Candida* to acrylic is considered to be a critical factor in the development of DS.<sup>20,21</sup> This adhesion occurs through the formation of biofilms on the denture surface that act as protective reservoirs that prevent *Candida* from being washed away by saliva or dislodgment forces.<sup>19</sup> Many studies have proven that both *Candida albicans* and *Candida glabrata* form these biofilms on denture surfaces.<sup>11,22-24</sup> Several studies have linked the surface characteristics of denture acrylics to the amount of *Candida* biofilm adhesion.<sup>25,26</sup> Ramage *et al.*<sup>21</sup> reported that imperfections on the denture surface contribute to an increase in the adhesion of *Candida*, which becomes imbedded within these imperfections. Other studies have also confirmed that surface roughness and surface crevices facilitate *Candida* colonization on denture surfaces.<sup>27</sup> In a review, Bidra *et al.*<sup>28</sup> reported that decreasing the porosity decreases *Candida* adhesion. Conventional heat-cured poly(methyl methacrylate) (PMMA) is the most popular

material for dentures.<sup>29</sup> It has been proven that this curing method increases the number of pores in the denture surface.<sup>29</sup>

In 1994, the first report in English to discuss the use of computer-aided technology (CAD/CAM) in the fabrication of complete denture with rapid prototyping technology was published.<sup>30</sup> Numerous CAD/CAM denture systems appear in the market, the dentures are milled from pre-polymerized pucks of resin.<sup>31,32</sup> CAD/CAM-fabricated complete dentures have several advantages over conventionally fabricated complete dentures.<sup>28</sup> One of these is a decrease in porosity because with CAD/CAM, the denture base is formed from a prepolymerized block of acrylic resin.<sup>28</sup> This decrease in porosity might decrease the adhesion of *Candida* to the dentures.<sup>28</sup> Also CAD/CAM fabricated dentures release a small amount of monomer, which may affect microbial adhesion and trigger a mucosal allergy reaction, but this effect is not as statistically significantly as the conventional dentures.<sup>32</sup> Usually the internal surface of complete denture is not highly polished which may affect the roughness threshold of microbial adhesion.<sup>33</sup> Therefore, the aim of the present study was to compare the adhesion of *Candida* on the surfaces of CAD/CAM and conventionally fabricated complete denture bases. The null hypothesis was that there would be no difference in *Candida* adhesion between the CAD/CAM and conventionally fabricated complete denture bases.

## MATERIALS AND METHODS

Twenty discs of Pink acrylic resin denture bases were fabricated with CAD/CAM and conventional procedures. The specimens were divided into two groups: discs that were fabricated using the CAD/CAM procedure (Wieland Digital Denture Ivoclar Vivadent, Schaan, Liechtenstein) and discs that were fabricated using a conventional flasking and pressure-pack technique.

Ten discs were fabricated from PMMA acrylic resin denture base material (major.base20 heat-processed PMMA, Moncalieri (TO), Italy) using a conventional flasking and pressure-pack technique. A stainless steel disc-shaped mold (3 × 10 mm) was used to make the discs according to the manufacturer's instructions.

The discs were cleaned with a steam jet (Wasi-Steam Classic, Wassermann Dental-Maschinen, Hamburg, Germany) after the deflasking procedure. The excess flash was removed using carbide cutters (Black Hawk Cutter, Horeco, Hopf, Ringleb & Co. GmbH & CIE, Berlin, Germany). The surface was finished with waterproof paper. Next, polishing was performed with a polishing compact unit (Derotor, London, England) consisting of a polishing lathe, a 45-mm polishing brush, and a pleated buff nettle cloth (Renfert GmbH, Industrie-gebiet, Hilzingen, Germany) with pumice (Pumice CL 60, Coarse Grade, Whip Mix Corporation, Louisville, KY, USA). Finally, the discs were cleaned with water and soap using a regular toothbrush followed by a steam jet.

Ten discs of  $10 \times 3$  mm were designed using Zenotec CAD software (Wieland Digital Denture Ivoclar Vivadent, Schaan, Liechtenstein). PMMA blocks were used (opera system, Principauté de Monaco, French). Milling was performed using Zenotec select ion (Wieland Digital Denture Ivoclar Vivadent, Schaan, Liechtenstein). These discs were finished and polished following the same procedures used for the discs made with the conventional method.

For both CAD/CAM and conventional denture materials, 30 readings were taken from randomly selected spots on the surface of each disc and subjected to surface roughness analysis. The measurements were made using a non-contact optical three-dimensional profilometer (Contour GT-I, Bruker) (Fig. 1, Fig. 2). Roughness is expressed as the surface area roughness ( $S_a$ ,  $\mu\text{m}$ ).

*Candida* isolates were subcultured on Sabouraud dextrose agar (SDA) (Oxoid, Hampshire, UK) for 24 hours at  $37^\circ\text{C}$ . The isolates were identified to the species level using the germ tube test and API20C-AUX methods. For the preparation of the yeast suspensions, the cells were inoculated in Sabouraud dextrose broth (SDB) (Oxoid, UK) and incubated for 18 hours at  $37^\circ\text{C}$  with shaking at 150 rpm. The yeast cells were harvested by centrifugation at 3000 g for 10 min and washed twice with phosphate-buffered saline (PBS; pH 7.0). The cell density was adjusted to  $1 \times 10^7$  cells/mL in SDB.


Biofilm formation by the *Candida albicans* clinical isolates was investigated with the microtiter plate method, as described previously.<sup>34</sup> From the biofilm screening assays, four *Candida albicans* isolates (CA-1, CA-2, CA-3, and CA-4) were selected for the adherence assay based on their ability to form biofilms.

Biofilm-producing *Candida albicans* isolates were selected for the adherence assay. The discs were disinfected using 70% alcohol and washed with sterile distilled water before


use in the adherence assay. For the adherence assay, yeast cells from a fresh culture were added to the SDB medium to a final concentration of  $1 \times 10^7$  cells/mL. The discs of dental materials were placed in a 24-well tissue culture plate (Corning, St. Louis, MO, USA), and 1 mL of the yeast cell suspension was added. The plate was incubated for 90 min at  $37^\circ\text{C}$  with shaking at 75 rpm. After incubation, the discs were transferred to new wells and washed three times with PBS to remove the non-adherent cells. The adherent *Candida* cells were dislodged from the surfaces of the dentures in 2 mL of PBS by scraping and vortexing for 5 minutes. The cell suspension was then gently sonicated for 3 minutes and plated on SDA. The colony-forming unit (CFU) counts were determined after 24 hours of incubation at  $37^\circ\text{C}$ . The determinations of the CFU counts were repeated on three different occasions separately for the four *Candida albicans* isolates with fresh cultures and adherence to the two different denture materials. The number of adherent cells is expressed as CFU/mL.

*Candida* was applied to the two types of discs (20 discs) and allowed to adhere as described above. After washing, the discs were stained with acridine orange (AO) (Sigma Aldrich, St. Louis, MO, USA) for 5 minutes, and the excess stain was gently rinsed off with PBS. The discs were examined under a fluorescent microscope (SMZ25, Nikon, Tokyo, Japan). Images were captured and analyzed using NIS-Elements imaging and analysis software (Nikon, Tokyo, Japan) (Fig. 3, Fig. 4).


Descriptive statistics were used to describe the *Candida albicans* isolate adhesion values for the conventional and CAD/CAM complete dentures. Student's t test was used to compare the adhesion of the *Candida albicans* isolates and the surface roughnesses between the CAD/CAM and conventional complete denture bases. A *P* value of  $< 0.5$  was considered statistically significant.




**Fig. 1.** Surface roughness of the CAD/CAM complete denture base.



**Fig. 2.** Surface roughness of the conventional complete denture base.



**Fig. 3.** *Candida* cells adhered to the conventional discs (stained with acridine orange).



**Fig. 4.** *Candida* cells adhered to the CAD/CAM discs (stained with acridine orange).

## RESULTS

This study assessed the adherence of *Candida albicans* to the surface of denture bases materials manufactured in two different ways. Table 1 presents the mean *Candida albicans* isolate adhesion values and their standard deviations for the conventional and CAD/CAM complete dentures. The conventional complete denture surface exhibited a higher adherence of *Candida albicans* isolates than did the CAD/CAM surface. The percentage of reduction in the adhesion of *Candida albicans* (CA-1, CA-2 and CA-3) on the CAD/CAM complete dentures was significantly lower than on the conventional dentures ( $P < .05$ ).

Table 2 presents the surface roughness of the complete denture surface. The conventional complete denture surface exhibited a surface roughness that was significantly greater than that of the CAD/CAM dentures.

The adherence ability was also assessed with acridin orange staining and observation under a fluorescent microscope. The number of yeast cells that adhered to the CAD/CAM discs was lower than the number that adhered to the conventional discs. This microscopic observation is in agreement with and confirms the CFU count. Four different *Candida albicans* isolates were used in this study to ensure that the outcome of the study was not influenced by biological differences in the *Candida* strains.

**Table 1.** Adhesion of *Candida albicans* isolates (CA-1 to CA-4) to the conventional and CAD/CAM discs

<i>Candida albicans</i> isolates	Conventional CFU/mL		CAD/CAM CFU/mL		% Reduction in adherence ( $\pm$ SD)	<i>P</i> value
	Mean	SD	Mean	SD		
CA-1	$2.3 \times 10^3$	$8.4 \times 10^2$	$1.1 \times 10^3$	$6.0 \times 10^2$	$51.7 \pm 17.1$	.0364
CA-2	$5.4 \times 10^3$	$1.6 \times 10^2$	$2.1 \times 10^3$	$8.7 \times 10^2$	$60.2 \pm 17.8$	.0041
CA-3	$2.0 \times 10^3$	$9.7 \times 10^2$	$1.2 \times 10^3$	$8.8 \times 10^2$	$47.2 \pm 24.8$	.0448
CA-4	$2.4 \times 10^3$	$1.1 \times 10^3$	$1.5 \times 10^3$	$7.2 \times 10^2$	$35.7 \pm 19.1$	.0648

**Table 2.** Comparison of the surface roughness of the complete denture surface (CAD/CAM vs. conventional)

Complete denture surface	Mean ( $\mu$ m)		SD ( $\mu$ m)	<i>P</i> value
	Sa			
CAD/CAM	0.037		0.001	
Conventional	0.073		0.015	.020

## DISCUSSION

The null hypothesis of this study was rejected because there was a difference in *Candida* adhesion between the CAD/CAM and the conventionally fabricated complete denture bases. In the present study, the adhesion of *Candida albicans* to the CAD/CAM and conventionally fabricated complete denture base surfaces was evaluated. The CFU count, which reflects cell adherence to the denture base, was used to assess the difference in adherence. Interestingly, *Candida albicans* exhibited differing adherence ability to the two different denture bases. *Candida albicans* adhered to the CAD/CAM base with a lower affinity than it did to the conventional denture base, which had greater surface roughness than CAD/CAM base.

The mechanism by which *Candida* species cause denture stomatitis can be summarized as follows. *Candida* can form biofilms on mucosal and denture surfaces that promote plaque deposition on the denture surface.<sup>9</sup> This deposition causes the mucosa to be continuously exposed to the microorganisms in the biofilm, which eventually causes DS.<sup>9</sup> These biofilms are important contributors to the development of DS.<sup>35</sup> *Candida albicans* is the most frequently isolated species in such biofilms.<sup>9,11,12,19</sup> The capability of *Candida albicans* to adhere to and form biofilms on PMMA varies.<sup>36</sup> The presence of a denture in the oral cavity facilitates the adherence of *Candida albicans* and causes infection.<sup>37</sup>

The reasons for the popularity of PMMA include its ease of handling, low cost, and esthetics.<sup>38</sup> However, it has many disadvantages, including its dimensional instability, residual monomer content, weak strength, water absorption, color instability, and porosity. Porosity is considered to be a shortcoming when it exceeds 11% because at this point, the mechanical properties and esthetics are compromised, and the material becomes a reservoir for microorganisms.<sup>29</sup> In 1968, the Academy of Denture Prosthetics stated that dentures should be free of pores to ensure adequate cleaning and resistance to stains and the adherence of microorganisms.<sup>38</sup> According to the American Dental Association's specifications for the porosity of denture base polymers, "there shall be no bubbles or voids when viewed without magnification".<sup>39</sup> Conventional heat-cured PMMA is the most common curing technique.<sup>29</sup> Porosity in heat-cured PMMA denture bases is an unfavorable result. Porosity can be caused by: air trapped during mixing, monomer contraction during polymerization, monomer vaporization associated with the exothermic reaction and the presence of residual monomer, insufficient mixing of monomer and polymer, a processing temperature higher than 74°C, the way the mold is packed, and inadequate compression on the flask.<sup>40-43</sup> The surface characteristics of the denture might contribute to an increase in *Candida* colonization due to hydrophobicity and roughness.<sup>25,26</sup>

Roughness is an important factor; the rougher the surface, the greater the *Candida* colonization will be.<sup>25</sup> There are several methods and devices available to measure the surface roughness, including visual assessments, scanning elec-

tron microscopy, profilometry, laser specular reflectance, and atomic force microscopy.<sup>44</sup> Profilometry is a common device for measuring surface roughness.<sup>45</sup> Profilometry can be performed with either contact or non-contact methods.<sup>46</sup> In this study, a non-contact optical three-dimensional profilometer was used. The non-contact method uses a laser or light beam to obtain a surface profile.<sup>47</sup> Kukiattrakoon *et al.*<sup>47</sup> claimed that one of the disadvantages of the contact method is that it can damage the surface by producing scratches. However, one study reported that not all irregularities in specimens can be penetrated by the sensor needle of a mechanical profilometer.<sup>48</sup> In the present study, an optical laser profilometer that provided a three-dimensional profile was used. According to Joniot *et al.*,<sup>49</sup> this method provides a non-contact, non-destructive, and rapid quantitative measurement of surface roughness.

As mentioned earlier, increased porosity has been proven to increase microorganism colonization.<sup>48,50</sup> Over the past several years, many attempts have been made to improve both the material properties and the curing and processing techniques.<sup>29</sup> The advantage of the CAD/CAM method over the conventional method is that a prepolymerized block of acrylic resin is used to mill the denture base.<sup>28</sup> The elimination of mixing used in the conventional procedures will decrease the porosity, which will ultimately decrease *Candida* adhesion. This study is considered one of the first studies that used microbiological assay comparing CAD/CAM and conventional procedure to fabricate dentures.

## CONCLUSION

Alterations of denture surface characteristics, such as porosity and surface roughness, contribute to a decrease in *Candida* adhesion, which ultimately decreases the risk of denture stomatitis. The surface characteristics of complete dentures fabricated with the CAD/CAM procedure exhibited promising potential for reducing the adherence of *Candida* to the denture base surface. Moreover, the adhesion of *Candida albicans* to the surfaces is significantly affected by the interactions with other microorganisms in the oral cavity. Therefore, further research is needed to fully determine the difference in adhesion to the surface of these denture base materials in complex *Candida* and bacterial models beside *in vivo* studies. Also different CAD/CAM systems with different surface roughness can be tested.

## ORCID

Afnan F. Alfouzan <https://orcid.org/0000-0003-2535-4641>

## REFERENCES

1. Cunha-Cruz J, Hujuel PP, Nadanovsky P. Secular trends in socio-economic disparities in edentulism: USA, 1972-2001. *J Dent Res* 2007;86:131-6.
2. Emami E, de Souza RF, Kabawat M, Feine JS. The impact of

- edentulism on oral and general health. *Int J Dent* 2013;2013:498305.
3. Dye BA, Li X, Thornton-Evans G. Oral health disparities as determined by selected healthy people 2020 oral health objectives for the United States, 2009-2010. *NCHS Data Brief* 2012;(104):1-8.
  4. Douglass CW, Shih A, Ostry L. Will there be a need for complete dentures in the United States in 2020? *J Prosthet Dent* 2002;87:5-8.
  5. Gottfredsen K, Walls AW. What dentition assures oral function? *Clin Oral Implants Res* 2007;18:34-45.
  6. Martori E, Ayuso-Montero R, Martinez-Gomis J, Viñas M, Peraire M. Risk factors for denture-related oral mucosal lesions in a geriatric population. *J Prosthet Dent* 2014;111:273-9.
  7. de Oliveira CE, Gasparoto TH, Dionísio TJ, Porto VC, Vieira NA, Santos CF, Lara VS. *Candida albicans* and denture stomatitis: evaluation of its presence in the lesion, prosthesis, and blood. *Int J Prosthodont* 2010;23:158-9.
  8. Shulman JD, Rivera-Hidalgo F, Beach MM. Risk factors associated with denture stomatitis in the United States. *J Oral Pathol Med* 2005;34:340-6.
  9. Gendreau L, Loewy ZG. Epidemiology and etiology of denture stomatitis. *J Prosthodont* 2011;20:251-60.
  10. Sadig W. The denture hygiene, denture stomatitis and role of dental hygienist. *Int J Dent Hyg* 2010;8:227-31.
  11. Yigit N, Aktas E, Dagistan S, Ayyildiz A. Investigating biofilm production, coagulase and hemolytic activity in *Candida* species isolated from denture stomatitis patients. *Eurasian J Med* 2011;43:27-32.
  12. Coco BJ, Bagg J, Cross LJ, Jose A, Cross J, Ramage G. Mixed *Candida albicans* and *Candida glabrata* populations associated with the pathogenesis of denture stomatitis. *Oral Microbiol Immunol* 2008;23:377-83.
  13. Ramage G, VandeWalle K, López-Ribot JL, Wickes BL. The filamentation pathway controlled by the Efg1 regulator protein is required for normal biofilm formation and development in *Candida albicans*. *FEMS Microbiol Lett* 2002;214:95-100.
  14. Mizugai H, Isogai E, Hirose K, Chiba I. Effect of denture wearing on occurrence of *Candida* species in the oral cavity. *J Appl Res* 2007;7:250-4.
  15. Samaranayake LP. Oral mycoses in HIV infection. *Oral Surg Oral Med Oral Pathol* 1992;73:171-80.
  16. Quirynen M, Marechal M, Busscher HJ, Weerkamp AH, Darius PL, van Steenberghe D. The influence of surface free energy and surface roughness on early plaque formation. An *in vivo* study in man. *J Clin Periodontol* 1990;17:138-44.
  17. Sumi Y, Nagaosa S, Michiwaki Y, Sunakawa M, Miura H. Comparative study of denture and pharyngeal bacterial flora of dependent elderly. *Jpn J Gerodont* 2001;16:171-8.
  18. Kumamoto CA, Vences MD. Alternative *Candida albicans* lifestyles: growth on surfaces. *Annu Rev Microbiol* 2005;59:113-33.
  19. Ramage G, Tomsett K, Wickes BL, López-Ribot JL, Redding SW. Denture stomatitis: a role for *Candida* biofilms. *Oral Surg Oral Med Oral Pathol Oral Radiol Endod* 2004;98:53-9.
  20. Spratt DA, Pratten J. Biofilms and the oral cavity. *Rev Environ Sci Biotechnol* 2003;2:109-20.
  21. Ramage G, Martínez JP, López-Ribot JL. *Candida* biofilms on implanted biomaterials: a clinically significant problem. *FEMS Yeast Res* 2006;6:979-86.
  22. Chandra J, Mukherjee PK, Leidich SD, Faddoul FF, Hoyer LL, Douglas LJ, Ghannoum MA. Antifungal resistance of candidal biofilms formed on denture acrylic *in vitro*. *J Dent Res* 2001;80:903-8.
  23. Kumar CP, Menon T. Biofilm production by clinical isolates of *Candida* species. *Med Mycol* 2006;44:99-101.
  24. Ramage G, Vande Walle K, Wickes BL, López-Ribot JL. Standardized method for *in vitro* antifungal susceptibility testing of *Candida albicans* biofilms. *Antimicrob Agents Chemother* 2001;45:2475-9.
  25. Radford DR, Sweet SP, Challacombe SJ, Walter JD. Adherence of *Candida albicans* to denture-base materials with different surface finishes. *J Dent* 1998;26:577-83.
  26. Hazen KC. Participation of yeast cell surface hydrophobicity in adherence of *Candida albicans* to human epithelial cells. *Infect Immun* 1989;57:1894-900.
  27. von Fraunhofer JA, Loewy ZG. Factors involved in microbial colonization of oral prostheses. *Gen Dent* 2009;57:136-43; quiz 144-5.
  28. Bidra AS, Taylor TD, Agar JR. Computer-aided technology for fabricating complete dentures: systematic review of historical background, current status, and future perspectives. *J Prosthet Dent* 2013;109:361-6.
  29. Singh S, Palaskar JN, Mittal S. Comparative evaluation of surface porosities in conventional heat polymerized acrylic resin cured by water bath and microwave energy with microwavable acrylic resin cured by microwave energy. *Contemp Clin Dent* 2013;4:147-51.
  30. Maeda Y, Minoura M, Tsutsumi S, Okada M, Nokubi T. A CAD/CAM system for removable denture. Part I: Fabrication of complete dentures. *Int J Prosthodont* 1994;7:17-21.
  31. Kattadiyil MT, Goodacre CJ, Baba NZ. CAD/CAM complete dentures: a review of two commercial fabrication systems. *J Calif Dent Assoc* 2013;41:407-16.
  32. Steinmassl PA, Wiedemair V, Huck C, Klauzner F, Steinmassl O, Grunert I, Dumfahrt H. Do CAD/CAM dentures really release less monomer than conventional dentures? *Clin Oral Investig* 2017;21:1697-705.
  33. Bollen CM, Lambrechts P, Quirynen M. Comparison of surface roughness of oral hard materials to the threshold surface roughness for bacterial plaque retention: a review of the literature. *Dent Mater* 1997;13:258-69.
  34. Silva S, Henriques M, Martins A, Oliveira R, Williams D, Azeredo J. Biofilms of non-*Candida albicans* *Candida* species: quantification, structure and matrix composition. *Med Mycol* 2009;47:681-9.
  35. Budtz-Jørgensen E. Etiology, pathogenesis, therapy, and prophylaxis of oral yeast infections. *Acta Odontol Scand* 1990;48:61-9.
  36. Chandra J, Kuhn DM, Mukherjee PK, Hoyer LL, McCormick T, Ghannoum MA. Biofilm formation by the fungal pathogen *Candida albicans*: development, architecture, and drug resis-

- tance. *J Bacteriol* 2001;183:5385-94.
37. Chaffin WL, López-Ribot JL, Casanova M, Gozalbo D, Martínez JP. Cell wall and secreted proteins of *Candida albicans*: identification, function, and expression. *Microbiol Mol Biol Rev* 1998;62:130-80.
  38. Final report of the workshop on clinical requirements of ideal denture base materials. The Academy of Denture Prosthetics. *J Prosthet Dent* 1968;20:101-5.
  39. Revised American Dental Association specification no. 12 for denture base polymers. *J Am Dent Assoc* 1975;90:451-8.
  40. Wolfaardt JF, Cleaton-Jones P, Fatti P. The occurrence of porosity in a heat-cured poly (methyl methacrylate) denture base resin. *J Prosthet Dent* 1986;55:393-400.
  41. Keller JC, Lautenschlager EP. Porosity reduction and its associated effect on the diametral tensile strength of activated acrylic resins. *J Prosthet Dent* 1985;53:374-9.
  42. al Doorri D, Huggett R, Bates JF, Brooks SC. A comparison of denture base acrylic resins polymerised by microwave irradiation and by conventional water bath curing systems. *Dent Mater* 1988;4:25-32.
  43. Compagnoni MA, Barbosa DB, de Souza RF, Pero AC. The effect of polymerization cycles on porosity of microwave-processed denture base resin. *J Prosthet Dent* 2004;91:281-5.
  44. Campbell SD. Evaluation of surface roughness and polishing techniques for new ceramic materials. *J Prosthet Dent* 1989;61:563-8.
  45. Jung M. Finishing and polishing of a hybrid composite and a heat-pressed glass ceramic. *Oper Dent* 2002;27:175-83.
  46. Whitehead SA, Shearer AC, Watts DC, Wilson NH. Comparison of two stylus methods for measuring surface texture. *Dent Mater* 1999;15:79-86.
  47. Kukiattrakoon B, Hengtrakool C, Kedjarune-Leggat U. Effect of acidic agents on surface roughness of dental ceramics. *Dent Res J (Isfahan)* 2011;8:6-15.
  48. Yazici AR, Müftü A, Kugel G. Three-dimensional surface profile analysis of different types of flowable restorative resins following different finishing protocols. *J Contemp Dent Pract* 2007;8:9-17.
  49. Joniot SB, Grégoire GL, Auther AM, Roques YM. Three-dimensional optical profilometry analysis of surface states obtained after finishing sequences for three composite resins. *Oper Dent* 2000;25:311-5.
  50. Kasina SP, Ajaz T, Attili S, Surapaneni H, Cherukuri M, Srinath HP. To evaluate and compare the porosities in the acrylic mandibular denture bases processed by two different polymerization techniques, using two different brands of commercially available denture base resins - an in vitro study. *J Int Oral Health* 2014;6:72-7.